



### Heat Shrinkable Tubing 2:1 - Elastomer

#### SE28

SE28 is used for long-term protection of cables and wire harnesses in military equipment, motor sports, and aviation.

#### Features and Benefits

- Flexible, high performance elastomeric heat shrink tubing
- Used in aerospace, defence, railway and automotive applications
- Resistant to diesel fuel, aviation and hydraulic fluids
- Provides a reliable protection against abrasion and mechanical damage
- Very suitable for protecting cables and wire harnesses



SE28 tubing.

<b>MATERIAL</b>	Elastomer, cross-linked (POA)
<b>Shrink Ratio</b>	2:1
<b>Operating Temperature</b>	-75 °C to +150 °C
<b>Minimum Shrink Temperature</b>	+170 °C
<b>Longitudinal change after shrinkage</b>	-10 % max.
<b>Dielectric Strength</b>	20 kV/mm
<b>Flammability</b>	VG 95343
<b>Specifications</b>	NF F 00-608, SAE - AMS - DTL-23053, VG 95343



SE28 is mainly used in high performance applications.



Heat Shrinkable Tubing 2:1

TYPE	Supplied Ø D min.	Recov. Ø d max.	Wall (WT)	Reel Length	Colour	Designation as per VG-Norm	Article-No.
SE28 3,2/1,6	3.2	1.6	0.70	150 m	Black (BK)	VG 95343 T 05 D 001 A	342-20000
SE28 4,8/2,4	4.8	2.4	0.80	60 m	Black (BK)	VG 95343 T 05 D 002 A	342-20010
SE28 6,4/3,2	6.4	3.2	0.90	60 m	Black (BK)	VG 95343 T 05 D 003 A	342-20020
SE28 9,5/4,8	9.5	4.8	1.00	60 m	Black (BK)	VG 95343 T 05 D 004 A	342-20030
SE28 12,7/6,4	12.7	6.4	1.20	60 m	Black (BK)	VG 95343 T 05 D 005 A	342-20040
SE28 19,0/9,5	19.0	9.5	1.40	30 m	Black (BK)	VG 95343 T 05 D 006 A	342-20050
SE28 25,4/12,7	25.4	12.7	1.80	30 m	Black (BK)	VG 95343 T 05 D 007 A	342-20060
SE28 38,0/19,0	38.0	19.0	2.40	30 m	Black (BK)	VG 95343 T 05 D 008 A	342-20070
SE28 51,0/25,4	51.0	25.4	2.80	30 m	Black (BK)	VG 95343 T 05 D 009 A	342-20080
SE28 76,0/38,0	76.0	38.0	3.20	15 m	Black (BK)	VG 95343 T 05 D 010 A	342-20090
SE28 101,2/51,0	102.0	51.0	3.50	10 m	Black (BK)	VG 95343 T 05 D 011 A	342-20100

All dimensions in mm. Subject to technical changes.  
Minimum Order Quantity (MOQ) may differ from package content.



For product specific approvals and specifications please refer to the Appendix.